

# junction | table



## Content Inventory

✓ 1,000 ppm

No RN	Wood dust (soft wood)	% by Weight: 60.348%
12597-69-2	Steel	% by Weight: 22.001%
9003-35-4	Phenol, polymer with formaldehyde	% by Weight: 5.729%
25036-13-9	Urea, polymer with formaldehyde and 1,3,5-triazine-2,4,6-triamine	% by Weight: 5.729%
9003-08-1	1,3,5-Triazine-2,4,6-triamine, polymer with formaldehyde	% by Weight: 1.91%
9004-34-6	Cellulose	% by Weight: 1.91%
9002-86-2	Polyvinyl chloride	% by Weight: 0.682%
1344-28-1	Aluminum Oxide	% by Weight: 0.382%
50-00-0	Formaldehyde (gas)	% by Weight: 0.382%
25036-25-3	Phenol, 4,4'-(1-methylethylidene)bis-, polymer with 2,2'- [(1-methylethylidene) bis(4,1-phenyleneoxymethylene)]bis[oxirane]	% by Weight: 0.274%
12597-69-2	Steel	% by Weight: 0.19%
1317-65-3	Calcium Carbonate	% by Weight: 0.18%
6422-86-2	Di(2-ethylhexyl) terephthalate	% by Weight: 0.158%

